




Vendor: 	STYRENE PARK OFFSITE PAINTING INSPECTION REPORT	Owner: 	Report No. : FPA-HX127-RU0001A-E02-P Date: 4/11/2025 SHEET 1 OF 1
--	--	---	--

Contract No.:	-	P.O.No.:	EI027-FPA-VD-QC-PRO-008
Project No.:	HX 127	Item No.:	RU0001A-E02
Paint Layer	As per Spec:	Humidity (%)	Project Spec
	Paint Type DFT μm Ral No.	Amb. temp. °C Surface Temp. °C	Paint Specification No.:
		Min. Max. Min. Max.	Dew Point (°C)
			MEK. Test: Adhesion Total DFT μm
			Acc. Rej. Acc. Rej. μm Measured DFT μm Manufa Batch
			Min. Max. Ave.
Primer:	Zinc Rich Epoxy 70 -	25% 15 20 17 24	3 - - Acc. - 70 68 78 73 14031
Intermediate	Epoxy polyamide MIO filled 100 -	20% 16 21 15 20	4 - - Acc. - 170 164 178 171 14031
Top Coating	Aliphatic Polyurethane 50 7038	22% 15 18 18 23	3 - - Acc. - 225 218 230 224 14031

JUDGEMENT: SATISFACTORY UNSATISFACTORY

FPA QC.	TPI 	OWNER
NAME:  DATE: SIGNATURE:	NAME:  DATE: SIGNATURE:	NAME: DATE: SIGNATURE: