








OWNER:  شرکت سست و سویی توستر ایرانیاان (سهایی نفاان)	BUSHEHR PETROCHEMICAL COMPANY MEG PLANT						EPC CONTRACTOR:		
	SURFACE PREPARATION AND PAINTING PROCEDURE						 Chagalesh-Enerchimi-Steam Joint Venture BUPC-MEG PLANT PROJECT		
MC :  شرکت سست و سویی توستر ایرانیاان (سهایی نفاان)									
	Project	Area	Phase	Unit	Dis.	Doc.	Seq.	Contract No : 52-98/445	
Owner Document Number: 17811-18	BU	20	VD	303	PI	DCR	0010	Rev.:	Page
								05	1 of 8

SURFACE PREPARATION AND PAINTING PROCEDURE

05	03/08/2022	Approved for Construction	BK	KP	JR	
04	13/07/2022	Approved for Construction	KP	CL	JR	
03	24/01/2022	Approved for Construction	KP	LDM	PW	
02	29/10/2021	Approved for Construction	KP	LDM	PW	
01	20/09/2021	For approval	KP	LDM	PW	
00	07/12/2020	For approval	KP	LdM	PW	
Rev.	Date	Purpose of Issue	Prepared	Checked	Approved	AC Code
					Class: 1	Phase: P

OWNER:  شرکت سست و سوس آمو ایران (سهایی خاص)	BUSHEHR PETROCHEMICAL COMPANY MEG PLANT						EPC CONTRACTOR:  Chagalesh-Enerchimi-Steam Joint Venture BUPC-MEG PLANT PROJECT		
	SURFACE PREPARATION AND PAINTING PROCEDURE						 Netherlands		
MC :  شرکت سست و سوس آمو ایران (سهایی خاص)	Project	Area	Phase	Unit	Dis.	Doc.	Seq.	Contract No : 52-98/445	
Owner Document Number: 17811-18	BU	20	VD	303	PI	DCR	0010	Rev.:	Page
								05	3 of 8

1. References

Reference is made to the following documents.

- Offer 17811-COM

2. General

Quality of paint is guaranteed by Airpack

Our paint system is based on a or brush/roller application. Painting will be done by Airpack painting specialists. As offered, Airpack equipment will be painted according to the paint schedule below.

- Galvanized steel grating does not require painting. This is only galvanized part in this package.
- Zinc plated and stainless steel bolts do not require painting.
- Stainless steel 316 equipment does not require painting. There are no SS304 components
- Instrumentation paint will be according manufacture standard.





3. Surface preparation

- All structures and equipment are designed and built in accordance with ISO standards for high durability of the paint systems.
- All oil or grease shall be removed by washing the item to be painted with appropriate solvents or any other suitable means before beginning blast cleaning operations. This includes bolt holes in piping assemblies.
- Weld spatter and remains of temporary welds, deposits or surface defects shall be eliminated appropriately.
- Airpack shall protect all equipment that is not to be painted or liable to be affected by the presence of abrasives or paint. Special attention will be paid to avoid splashes of zinc paint on equipment made of austenitic steels.
- Surface preparation shall be inspected by Airpack Quality Control prior to application of paint.

4. Blast cleaning of carbon steel

All surfaces to be coated, will be blast-cleaned according to:

- the grade of cleanliness, SA 2.5
- the surface profile, to be evaluated using SSPC-VIS 1
- as painting is Airpack standard, no blast clean record is available.

OWNER:  شرکت سست و سویی آرمو ایرلیان (سهامی عامه)	BUSHEHR PETROCHEMICAL COMPANY MEG PLANT						EPC CONTRACTOR:  Chagalesh-Enerchimi-Steam Joint Venture BUPC-MEG PLANT PROJECT		
	SURFACE PREPARATION AND PAINTING PROCEDURE						 Netherlands		
MC :  شرکت سست و سویی آرمو ایرلیان (سهامی عامه)	Project	Area	Phase	Unit	Dis.	Doc.	Seq.	Contract No : 52-98/445	
Owner Document Number: 17811-18	BU	20	VD	303	PI	DCR	0010	Rev.: 05	Page 4 of 8

After blast-cleaning, all dust must be removed using a vacuum cleaner before applying the paint. All blast-cleaned surfaces shall be coated before the deterioration of the "grade of cleanliness". In any case, any surface that has been blast-cleaned shall be coated on the same day.

5. Paint Application

Coating system will be from paint manufacturer Jotun.

The products shall be delivered in their original sealed packaging and stored in such conditions as to avoid their degradation. The packaging shall be clearly marked with the product description, the batch number, the fabrication date and the expiration date. Paint shall always be applied to surfaces that are dry, clean and degreased, for both coating on substrate and previous coat.

Painting work shall not proceed if:

- Temperature of the substrate is less than 3°C above the dew point;
- The relative humidity is more than 85% RH (90% RH for inorganic zinc silicates);
- The weather is rainy or foggy, except under shelter, and subject to verification of the atmospheric conditions;
- The minimum or maximum temperature of the ambient atmosphere and the substrate are outside the limits given in the product data sheets.

Application shall be by or brush/roller. Stripe coats shall be applied by brush to all angles, corners, and all the welds with the same product than this to be applied on the surface to be painted. Different colours shall be used for all successive coats of the paint system. The finishing coat of the required colour shall be opaque to cover the shade of the undercoat. The thickness of each coat, including frequency shall be checked by Airpack. The values will be recorded and made available.

6. Painting report





A paint report as attached (see attachment 1) will be provided with a final coating check during FAT. Dry film thickness will be checked using a calibrated Fisher Dual scope MPOR SN040003992. Calibration certificate will be made available during FAT.

7. Paint systems

For a detailed overview of each item please refer to below paint schedule.

8. Repair procedure

In case a deviation or non-conformity has been found, this will be repaired as per below procedure. Where the coating has been scratched off, flaked, or in any other way damaged as to hamper its protective function, the coating will be grinded off 5 cm around the defect

OWNER:  شرکت مست و سوزی آمو ایران لیان (سهایی نظامی)	BUSHEHR PETROCHEMICAL COMPANY MEG PLANT						EPC CONTRACTOR:  Chagalesh-Enerchimi-Steam Joint Venture BUPC-MEG PLANT PROJECT		
	SURFACE PREPARATION AND PAINTING PROCEDURE								
MC :  شرکت مست و سوزی آمو ایران لیان (سهایی نظامی)	Project	Area	Phase	Unit	Dis.	Doc.	Seq.	Contract No : 52-98/445	
Owner Document Number: 17811-18	BU	20	VD	303	PI	DCR	0010	Rev.: 05	Page 5 of 8





and paint will be re-applied to conform with the painting system defined in this painting procedure.

In case more than 5% of the equipment surface is not conform specifications, the entire part will be blasted and re-coated. Where blasting is not feasible, paint will be grinded off until the bare metal, after which it is re-coated.

Paint schedule

	MATERIAL	DESCRIPTION	SYSTEM	TDFT [μm]	FINAL COLOR
C1	Aluminium / cast iron	MAIN E-MOTORS	Mfr. std.	Mfr. std.	RAL-5010
C2	Carbon Steel	STRUCTURAL STEEL	1	320	RAL-1013
C3	Carbon Steel	VALVES <120°C	1	320	RAL-7035
C4	Carbon Steel	COOLER	1	320	RAL-7035
C5	Carbon Steel	PIPING COLD	1	320	RAL-7035
C6	Carbon Steel	PULSATION DAMPER COLD	1	320	RAL-7035
C7	Carbon Steel	PULSATION DAMPER COLD	3	320	RAL-7035
C8	Carbon Steel	PULSATION DAMPER HOT ²	3	150	RAL-9006 Aluminium
C9	Carbon Steel	COMPRESSOR HOT PARTS ²	3	150	RAL-9006 Aluminium
C10	Carbon Steel	COMPRESSOR	3	320	RAL-7035
C11	Carbon Steel	PRESSURE SAFETY VALVE	3	150	RAL-9006 Aluminium
C12	Carbon Steel	PIPING HOT ²	3	150	RAL-9006 Aluminium
C13	Aluminium	LOCAL CONTROL PANEL ¹	Mfr. std.	100	RAL-7035
C14	Aluminium	LOCAL MCC (POWER DISTRIBUTION PANEL) ¹	Mfr. std.	100	RAL-7032
C15	Stainless Steel	GENERAL	Not painted	-	

1. Possibilities for painting of materials with ATEX certification is limited, Paint details not available
2. Hot parts are painted with a special paint which is only available in Aluminum.

OWNER:  شرکت سست و سوس آیرو ایران (سهامی عامه)	BUSHEHR PETROCHEMICAL COMPANY MEG PLANT						EPC CONTRACTOR:  Chagalesh-Enerchimi-Steam Joint Venture BUPC-MEG PLANT PROJECT		
	SURFACE PREPARATION AND PAINTING PROCEDURE						 Netherlands		
MC :  شرکت سست و سوس آیرو ایران (سهامی عامه)	Project	Area	Phase	Unit	Dis.	Doc.	Seq.	Contract No : 52-98/445	
Owner Document Number: 17811-18	BU	20	VD	303	PI	DCR	0010	Rev.: 05	Page 6 of 8

Paint system 1 (acc. ISO 12944-2 C5M-H table S7.04, & Jotun)





- Structural steel & Carbon steel piping
- Surface preparation Sa 2½
- Temperatures up to 120°C

Layer	Type of paint	Make	DFT
1	epoxy mastic	Jotamastic Smart Pack	90 µm
2	epoxy mastic	Jotamastic Smart Pack	90 µm
3	epoxy mastic	Jotamastic Smart Pack	90 µm
4	Polyurethane	Hardtop XP	50 µm
		Total DFT	320 µm

Paint system 3

- High temperature / Carbon steel cycling use
- Surface preparation Sa 2½
- Temperatures -185 up to 650°C
- Available colours: Black, Grey and Aluminium effect

Layer	Type of paint	Make	DFT
1	Multipolymeric Matrix coating	Jotatemp	75 µm
2	Multipolymeric Matrix coating	Jotatemp	75 µm
		Total DFT	150 µm

OWNER:  شرکت مست و سوزی آمو ایرلیان (سهایی نایان)	BUSHEHR PETROCHEMICAL COMPANY MEG PLANT						EPC CONTRACTOR:  Chagalesh-Enerchimi-Steam Joint Venture BUPC-MEG PLANT PROJECT		
	SURFACE PREPARATION AND PAINTING PROCEDURE						 Netherlands		
MC :  شرکت مست و سوزی آمو ایرلیان (سهایی نایان)							Project	Area	Phase
Owner Document Number: 17811-18	BU	20	VD	303	PI	DCR	0010	Rev.: 05	Page 7 of 8

PAINT REPORT

Customer : ...
Purchase order number : ...
Equipment : ...
Equipment item no. : ...
Airpack ref. no. : XXXXX-COM
Serial no. : ...
Test location : Zierikzee
Test date : ...

Item : SKID
Paint system : 1

MEASUREMENTS According to Attachment #1

EXAMPLE

